



IKATES, s.r.o.

Laboratory for glass and building products testing

Tolstého 186, Řetenice, 415 03 Teplice, Czech Republic

tel.: +420 417 503 093 / +420 417 502 825

e-mail: ikates@ikates.cz, www.ikates.cz



Testing laboratory No.1139 accredited by Czech Accreditation Institute, o.p.s.

according to ČSN EN ISO/IEC 17025:2018

TEST REPORT

No. : 29 / 2023

Test item : **Insulating glass units**
- long term test method and requirements for moisture penetration according to ČSN EN 1279-2 (initial type test)

Client (address): **NEWMOS Glass Trading Ltd**
No:9 Ozgurluk Caddesi, Organize Sanayi Bolgesi,
Haspolat, Lefkosa, CYPRUS

Producer (address): **NEWMOS Glass Trading Ltd**
No. 9 Ozgurluk Caddesi, Organize Sanayi Bolgesi,
Haspolat, Lefkosa, CYPRUS

Place of test performance : **testing laboratory IKATES, s.r.o., Teplice**

Date of sample receiving : **2023-02-09**

Date of test performance : **2023-02-16 to 2023-05-11**

Date of issue : **2023-05-25**

Number of pages : **4**

Page No. : **1**

Manager of testing laboratory : **Jiří Stránský**



Results and/or information out of accreditation range and subcontracts are in the test report identified. Copying and translating, using of report for other purposes (advertisement, extracts from the report) only with consent of the laboratory. Without consent of the laboratory, this report can be reproduced whole only.

No. : 29 / 2023	Number of pages : 4
	Page No. : 2

Normative foundations :

ČSN EN 1279-2 (2019): Glass in building - Insulating glass units – Part 2: Long term test method and requirements for moisture penetration

Sampling :

Following test specimens of insulating glass units have been supplied to the testing laboratory :

Samples description provided by the producer	
IGU construction :	float glass clear 4 mm + 12 mm, Al + float glass clear 4 mm
Number of pieces and external dimensions :	15 pcs 352 x 502 mm x 20 mm
Production date :	2023-01-16
Glass (name, producer, type) :	float glass clear 4 mm; Şişecam
Spacer (material, name, producer) :	Aluminium, 12 mm, sawed, TEK METAL
Corner keys (name, producer, additional sealing) :	Plastic corner keys; ERPASAN KALIP PLASTIK
Joint (name, producer, additional sealing) :	-
Desiccant (name, producer, type, filled sides, T _c) :	Zeolan K, 3Å; Nedex, Turkey, 1,4 – 2,0 mm; 2 long sides; 17,9 %
Outer sealant (name, producer, type) :	IGK 130, polyurethane
Average sealant depth on spacer back (u) :	3,5 mm
Average sealant depth on glass surface (s) :	5 mm
Inner sealant (name, producer, type) :	Erpasan BU2000, polyisobutylene
Average sealant depth (r) :	2,5-3,0 mm
Mass of inner sealant / length and side (R):	2,5 g/m/side
Coating (name, producer) :	-
Edge deletion :	-
Gas filling (type) :	-
Closing of gap filling holes (type) :	-
Special features (e.g. inserts) :	-



No. : 29 / 2023	Number of pages : 4
	Page No. : 3

Metrological provision of tests :

Calibrated measuring gauges of testing laboratory were used during testing.

Climatic test was performed in the climatic chamber CTS controlled by the calibrated thermo- and hygrometer and by the validated software CID-PRO.

Determination of moisture content and adsorption capacity of desiccant was performed using of oven Tempra with calibrated thermocouples and verified laboratory balances KERN 770-14.

Test results :

External dimensions :	352 x 502 mm				
Total thickness before aging test :	19,9 mm				
Product name :	MOS GLASS - Insulated glass unit				
Corner construction :	sawed, plastic corner keys – butyllled				
Amount of desiccant (filled sides) :	2 long sides				
Average sealant depth on spacer back (u) :	6-7 mm				
Average sealant depth on glass surface (s) :	7-8 mm				
Average sealant depth (r) :	5-6 mm				
Edge deletion :	-				
Special features (e.g. inserts) :	-				
Initial moisture content T_i (%) :	1,27	1,40	1,23	1,36	
Average initial moisture content $T_{i, av}$ (%) :	1,32				
Final moisture content T_f (%) :	2,33	2,44	2,14	1,92	2,32
Average final moisture content $T_{f, av}$ (%) :	2,23				
Moisture penetration index I (%) :	6,14	6,79	4,98	3,68	6,08
Average moisture penetration index I_{av} (%) :	5,53				
Test passed :	YES				



No. : 29 / 2023	Number of pages : 4 Page No. : 4
-----------------	-------------------------------------

Statement : Test results, given in this report, apply only to the tested items as received. The test report does not replace other documents, e.g. administrative characters, issued by other bodies, according to particular regulations. The official version is in Czech language.

Distribution list :

2 x NEWMOS Glass Trading Ltd

1 x Laboratory for glass and building products testing IKATES, s.r.o. (archive)

Test results were approved by :

For correctness of the report is responsible :

Michal Hnilička

end of the test report

